

BOPP

PLAIN BROWN FILM FOR LOW C.O.F.

CODE PRL

Film is a special structure biaxially oriented polypropylene for printing and lamination applications. Film designed to meet the requirement of recycle film, Excellent one side slip, good dimensional stability, and good resistance to oil and grease.

TECHNICAL DATA

TYPICAL PROPERTIES	UNIT		TEST METHODS	TYPICAL VALUE	
THICKNESS	micron		Micrometer	30	40
YIELD	m ² /kg		ASTM D4321	36.63	27.47
G.S.M.	g/m ²		Analysis balance	27.30	36.40
DENSITY	g/cm ³		ASTM D-1505	0.91	0.91
AVERAGE THICKNESS VARIATION	%		ASTM E-252-78	± 3	± 3
TENSILE STRENGTH	N/mm ²	MD	ASTM D-882	110	110
	(min.)	TD		250	250
ELONGATION AT BREAK	%	MD	ASTM D-882	200	200
	(max.)	TD		60	60
DIMENSIONAL STABILITY	%	MD	ASTM D-1204 120 °C, 15 minutes	3.0	3.0
	(max.)	TD		4.0	4.0
C.O.F.	(max.)	T/T	ASTM D-1894	0.55	0.55
		NT/NT		0.30	0.30
HAZE	%(max.)		ASTM D-1003-61	2.5	2.5
GLOSS (angle 60°)	%(min.)		ASTM D-2457	145	145
WETTING TENSION	Dynes/cm	Treated side	ASTM D-2578	38	38
	(min.)				
WVTR	g/m ² .day	(max.)	ASTM E-398-03 38 °C, 90% RH	5	3
O ₂ TR	cm ³ /m ² .day.bar	(max.)	ASTM D-1434-82 23 °C, 0% RH, 1 atm	450	400

* For both side we treat one side 38 dynes/cm, other side 37 dyne/cm.

DESCRIPTION OF SUPPLY

PAPER CORE I.D. 76 mm (3 in.) 152 mm (6 in.)

ROLL OUTSIDE DIAMETER max. 600 mm

WIDTH RANGE 100 mm – 1500 mm. (width on request)

LENGTH RANGE standard 2000 m, 3000 m, 4000m and 6000 m.(length on request)

Our Product comply with U.S. 21 CFR F.D.A. Regulation Part 177.1520

The data and information contained herein are given purely as a guide. Technical information is furnished solely as reference concerning the mentioned product without any obligation, end users shall consider suitability for their own adoption & usage. As conditions of use may vary and are beyond our control, A.J. Plast Public Company Limited undertake on responsibility and liability for accuracy of any technical information and results obtained by usage of this product.