

BOPP PEARLIZED FILM

CODE OP

Film with both side heat sealable layer for VFFS/HFFS. Excellent slip and anti static property, good opacity.

TECHNICAL DATA

TYPICAL PROPERTIES	UNIT		TEST METHODS	TYPICAL VALUE	
THICKNESS	micron		Micrometer	40	50
YIELD	m ² /kg		ASTM D4321	32.62 - 38.70	26.34 - 30.64
DENSITY	g/cm ³		ASTM D-1505	0.68 - 0.73	0.68 - 0.73
THICKNESS TOLERANCE	micron		ASTM E-252-78	± 2	± 2
TENSILE STRENGTH	N/mm ²	MD	ASTM D-882	70	70
	(min.)	TD		150	150
ELONGATION AT BREAK	%	MD	ASTM D-882	120	120
	(min.)	TD		30	30
DIMENSIONAL STABILITY 120°C. 15 minutes	%	MD	ASTM D-1204	3.0	3.0
	(max.)	TD		2.0	2.0
SEALING TEMPERATURE	°C		1 BAR, 1 SEC	118-120	118-120
SEAL STRENGTH	N/15 mm (min.)		1 BAR, 1 SEC, 15 mm	2.0	2.0
C.O.F.	(max.)	T/T	ASTM D-1894	0.5	0.5
		NT/NT		0.5	0.5
OPACITY	% (min.)		Sheenopac meter	75	75
	% (min.)		Color meter	75	75
GLOSS (angle 60°)	% (min.)		ASTM D-2457	35	35
WETTING TENSION	Dynes/cm	Treated side	ASTM D-2578	38	38

* For both side we treat one side 38 dynes/cm, other side 37 dynes/cm.

DESCRIPTION OF SUPPLY

PAPER CORE I.D. 76 mm (3 in.) 152 mm (6 in.)

ROLL OUTSIDE DIAMETER max. 600 mm

WIDTH RANGE 100 mm – 1500 mm. (other width on request)

LENGTH RANGE standard 2000 m, 3000 m, 4000m and 6000 m. (other length on request)

Our Product comply with U.S. 21 CFR F.D.A. Regulation Part 177.1520

The data and information contained herein are given purely as a guide. Technical information is furnished solely as reference concerning the mentioned product without any obligation, end users shall consider suitability for their own adoption & usage. As conditions of use may vary and are beyond our control, A.J. Plast Public Company Limited undertake on responsibility and liability for accuracy of any technical information and results obtained by usage of this product.