

BOPP CO-EX MATT

CODE MTU

Film is a special structure biaxially oriented polypropylene for lamination applications. Film designed to meet the requirement, good dimensional stability, and high haze.

TECHNICAL DATA

TYPICAL PROPERTIES	UNIT	TEST METHODS	TYPICAL VALUE
THICKNESS	micron	Micrometer	20
YIELD	m ² /kg	ASTM D4321	64.94-60.24
G.S.M.	g/m ²	Analysis balance	16.60-15.40
DENSITY	g/cm ³	ASTM D-1505	0.77-0.83
THICKNESS TOLERANCE	micron	ASTM E-252-78	± 2
TENSILE STRENGTH	N/mm ²	ASTM D-882	110
	(min.)		170
ELONGATION AT BREAK	%	ASTM D-882	200
	(max.)		70
DIMENSIONAL STABILITY	%	ASTM D-1204 120 °C, 15 minutes	3.0
	(max.)		2.0
C.O.F.		MATT	0.6 ± 0.1
		GLOSS	0.5 ± 0.1
HAZE	%(min.)	ASTM D-1003-61	85
GLOSS (angle 85°)	%(max.)	ASTM D-2457	35
WETTING TENSION	Dynes/cm (min.)	GLOSS SIDE	ASTM D-2578
WVTR	g/m ² .day	(max.)	ASTM E-398-03 38 °C, 90% RH
O ₂ TR	cm ³ /m ² .day.bar	(max.)	ASTM D-1434-82 23 °C, 0% RH, 1 atm

DESCRIPTION OF SUPPLY

PAPER CORE I.D. 76 mm (3 in.) 152 mm (6 in.)

ROLL OUTSIDE DIAMETER max. 600 mm

WIDTH RANGE 100 mm – 1500 mm. (other width on request)

LENGTH RANGE standard 2000 m, 3000 m, 4000 m, and 6000 m. (length on request)

Our Product comply with U.S. 21 CFR F.D.A. Regulation Part 177.1520

The data and information contained herein are given purely as a guide. Technical information is furnished solely as reference concerning the mentioned product without any obligation, end users shall consider suitability for their own adoption & usage. As conditions of use may vary and are beyond our control, A.J. Plast Public Company Limited undertake on responsibility and liability for accuracy of any technical information and results obtained by usage of this product.